

# 中山市建远电子厂

## Characteristics of Materials

### 材料特性表



Materials	$\mu$ iac $\pm 25\%$	Practical frequency MHz	tan $\sigma$ / $\mu$ iac (X10-6)    MHZ		$\alpha$ $\mu$ r	Bms (mT)    (Oe)		Hc (Oe)	Tc (oC)	d (g/cm <sup>3</sup> )
					(20to60°C) (X10-6)					
362	1500	0.01~0.5	80	0.5	2~5	240	40	0.14	100	4.9
361	1000	0.01~0.5	40	0.5	3~5	270	40	0.2	100	4.9
391	650	0.01~0.5	60	0.5	7~12	290	40	0.2	135	4.8
392	400	0.1~2.0	65	2	10~30	290	40	0.48	150	4.8
393	350	0.05~2.0	70	2	5~15	300	40	0.34	150	4.8
351	100	0.5~20	300	20	4~12	280	40	6	300	4.8